

MULTI-LAYER FILTER ELEMENT

CROSS REFERENCE TO RELATED APPLICATIONS

This application is a continuation of international application no. PCT/EP00/03547, filed April 19, 2000 designating the United States of America, the entire disclosure of which is incorporated herein by reference. Priority is claimed based on Federal Republic of Germany patent application no. DE 199 17 690.6, filed April 19, 1999.

BACKGROUND OF THE INVENTION

The present invention relates generally to filter elements, and particularly to filter elements for filtering gases or liquids. Especially, the invention relates to multi-layer filter elements, in which several layers of filter media follow one another in succession in the direction of flow through the filter and in which all the individual layers are composed of synthetic fibers.

It is generally known to combine different filter materials in filter elements to produce optimum filter characteristics for the particles to be filtered and the liquid and/or gas which flows through the filter. For instance German patent application no. DE-A 44 43 158 discloses the use of a meltblown nonwoven web or fleece as the filter medium in a gas stream together with a carrier or support material that serves exclusively for stabilization.

Furthermore, US patent no. 5,591,335 (= WO 96/34673) discloses arranging a plurality of filter layers composed of a meltblown nonwoven web on a support layer in a hollow cylindrical filter element. Together, the layers form a replaceable filter element which can be utilized in a filter arrangement

US patent no. 5,496,627 and US patent no. 5,766,288 (= WO 95/17946) disclose the successive arrangement of filter media of synthetic fibers with graduated filter fineness. Here, the filter fineness of the filter layers increases in the direction of flow through the filter.

US patent no. 5,427,597 and US patent no. 5,591,335 (= WO 96/34673) disclose the arrangement of one or more filter layers composed of a nonwoven web produced by a meltblowing process on a support layer which serves to stabilize the filter material. The filter action of the support layer is negligible compared to that of the other layers.

Despite the efforts of the prior art, the heretofore available filter elements do not exhibit sufficient heat resistance and long-term stability to gaseous and liquid media to satisfy today's requirements, and there has remained a need for improved filter materials.

SUMMARY OF THE INVENTION

Thus, it is the object of the present invention to improve filter performance of the multilayer medium through improved adaptation or matching of the individual layers in terms of a pre-filtration/fine-filtration while maintaining the same filter permeability.

It is also an object of the invention to provide a multi-layer filter construction which exhibits an improved overall filter action and can maintain it over a long period of time.

These and other objects have been achieved by providing a multilayer filter element of the type described above in which the filter layers all exhibit successively increasing filter fineness in the direction of flow through the filter medium and at least one filter layer arranged on the inflow side is composed of a meltblown nonwoven web.

The use of such a filter layer of a meltblown nonwoven web enables the use of fibers having a fiber diameter which is reduced by up to an order of magnitude. This results in an improved particle retention capacity while maintaining the same fractional filtration efficiency or an improved fractional

filtration efficiency while maintaining the same particle retention capacity and thus achieves improved filter performance.

BRIEF DESCRIPTION OF THE DRAWINGS

The invention will be described in further detail hereinafter with reference to illustrative preferred embodiments shown in the accompanying drawings in which:

Fig. 1 is a schematic illustration of an example of an arrangement of three successive layers of filter media, and

Fig. 2 is a schematic illustration of an example of a star-folded filter material according to the invention.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

In contrast to the filter layers of the prior art, the filter layer 1 arranged on the outflow side (filtered side) of the filter material of the present invention is not made of cellulose. This allows the use of synthetic fibers with a fiber diameter that is reduced by up to an order of magnitude. In a particularly preferred embodiment, the synthetic fibers are polyester fibers.

Fig. 1 shows a multilayer filter element according to the invention. At least one filter layer 3 on the inflow side (unfiltered side) is made of a meltblown nonwoven web. Due to the use of fibers having a diameter of $< 3 \mu\text{m}$, which is reduced compared to the fibers of nonwoven filter webs produced by other techniques, nonwoven webs produced by the meltblown technique exhibit improved filter performance.

The starting material for the meltblown nonwoven web may be, for example, polypropylene (PP), especially for non-aggressive liquids, or polyether sulfone (PES), which is suitable also for filtering fuel or hydraulic oils up to a temperature of about 80°C . It is, however, preferred to use polyester fibers.

A progressive arrangement of successive filter layers with different degrees of filter fineness provides a pre-filter/fine-filter effect and thereby increases the performance of the overall system. Arranging the meltblown layer on the inflow side makes it possible to utilize the superior particle